



**MARINE  
CARE**

# CARECLEAN RUST

## Acidic cleaning product to remove:

- **Hardness stains and residues after tank cleaning operations**
- **Rust stains on paintwork**

### DESCRIPTION

Careclean Rust is based on phosphoric acid and non-ionic surfactants. Careclean Rust is used for the removal of hardness stains after tank cleaning operations, removal of rust stains on paintwork, cleaning of aluminum floor plates, copper and brass fittings and wooden decks.

### ADVANTAGE

- Effectively removes hardness stains
- Safe on most coatings and common metals
- Removes rust stains without risk to paintwork, ceramics, glass, wood, etc.
- Cleans and brightens aluminum and non-ferro metals with a shiny result

### APPLICATION

- Removal of hardness stains in cargo tanks
- Removal of iron ore, limestone (carbonates), magnesite from cargo holds
- Removal of rust stains on paintwork, wood and plastics
- Cleaning of aluminum floor plates in the engine room
- Cleaning of copper, brass and bronze parts

### DIRECTIONS FOR USE

#### *Tank Cleaning*

In case hardness stains and/or residues are present after completion of tank cleaning operations, either inject 0,5 % Careclean Rust directly into the automatic washing system for approx. 30 minutes to 1 hour (with a minimum of 1 cycle) or circulate a 0,5 % solution of Careclean Rust in freshwater at a temperature is 75 - 85 °C for 1 hour. Careclean Rust is suitable to be used on epoxy and stainless steel coatings, it is not suitable to be used in zinc coated tanks.

- **Eco-friendly**
- **Biodegradable**
- **Suitable on most metals and coatings**
- **Approved by:**
  - > IMO
  - > Marinfloc
  - > Coating manufacturers

Revision	4.0	Document number	PDS-08-147
Date of issue	12-08-2022	Page	1 of 2

**MARINE CARE BV**  
Oude Maasweg 35  
Port number #4005  
3197 KJ Botlek - Rotterdam  
The Netherlands  
T. +31 (0)10 2950342  
F. +31 (0)10 2950345  
E. [supply@marinecare.nl](mailto:supply@marinecare.nl)



# MARINE CARE

## CARECLEAN RUST

### Cargo Hold Cleaning

Careclean Rust is used to clean cargo holds after cargoes such as iron ore, limestone (carbonates) and magnesite and to remove any white residues from caustic cleaners or hardness deposits from seawater. After sweeping and demucking apply Careclean Rust in a 10-50% solution depending on the contamination. Let the product soak for 30 minutes making sure not to let the solution dry on the surface. Then spray off with water.

Careclean Rust can be applied with the *Caretech Application Kit*.

### Paintwork

Dilute Careclean Rust to a 10 - 20 % solution in water. Apply the solution by brush or spray using plastic equipment. Leave to soak for 10 - 20 minutes. Rinse off using a powerful water jet and a brush, if necessary.

### General

In most cases Careclean Rust is applied by brush diluted with water to a 10 - 50 % solution. The reaction time has to be 5 - 10 minutes.

Small objects can be soaked in a plastic container. After cleaning, rinse items thoroughly with a water jet.

### DOSAGE

Tank cleaning	0,5 - 3 %	solution
Hold cleaning	10 - 50 %	solution
Paintwork	10 - 20 %	solution
General	10 - 50 %	solution

### PROPERTIES

Article number	14203 / 16203
pH	2,0
Density	1,28 g/cm <sup>3</sup>
Flashpoint	Not applicable
Physical state	Liquid

### APPROVALS

- IMO approved in accordance with MEPC 590
- Marinfloc Approved OWS Compatible
- Major coating manufacturers. Deviations in temperature, exposure time and concentration to the above stated can vary per coating type, consult the coating manufacturers user guidelines.

For detailed information on safety and health, please refer to the Material Safety Data Sheet MSDS and/or product label.

- Eco-friendly
- Biodegradable
- Suitable on most metals and coatings
- Approved by:
  - > IMO
  - > Marinfloc
  - > Coating manufacturers

Revision	4.0	Document number	PDS-08-147
Date of issue	12-08-2022	Page	2 of 2

This information is based on data that we believe to be accurate and reliable and is intended to be used by persons having the knowledge and skill to apply this product properly. We assume no responsibility for results or damages incurred from their use by the Buyer. No liability (including liability for negligence) will attach to Marine Care or its servants or agents arising out of or in connection with or in relation to this product information.

**MARINE CARE BV**  
Oude Maasweg 35  
Port number #4005  
3197 KJ Rotterdam Botlek  
The Netherlands  
T. +31 (0)10 2950342  
F. +31 (0)10 2950345  
E. [supply@marinecare.nl](mailto:supply@marinecare.nl)